

RS12 NR



NR SHEETING HIGH PERFORMANCE

FEATURES

Natural rubber, para quality, translucent, with excellent mechanical properties.

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general purpose applications in contact with:

- maximum temperature 50 °C: water, water washing, alkaline and salt solutions, acids and oxidizing non oxidizing, alkali base concentration ≤50%, non food alcohol
- maximum temperature 20 °C: acetones

Cutting into skirtboard and scrappers for conveyors belts, rubber sleeves, etc.

Mineral processing equipment linings, such as operating cyclones, hydrocyclones and sand treatment processes.

ADVANTAGES

- ▮ Very good mechanical properties (tensile strength, tear resistance, etc.) and at the same time, easy material to work with
- ▮ Good properties to support high mechanical strains
- ▮ Great elasticity allowing important deformations
- ▮ Resistance to fine grained particles wear projection (sand, blasting)
- ▮ Good electrical properties
- ▮ Good resistance to acids, bases and salts
- ▮ Good ratio quality/price

BENEFITS

- ▮ Functionality
- ▮ Comfort
- ▮ Service life
- ▮ Economy

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

	Measured characteristics	Standard	Value	
MECHANICAL				
	Rubber compound - beige		NR	
	Density		1.0 ±0.05	g/cm ³
	Hardness	ASTM D2240	40 ±5	Shore A
	Tensile strength	ISO 37	≥18	MPa
	Elongation at break	ISO 37	≥600	%
	Tear resistance	ISO 34-1	≥25	N/mm
	Abrasion resistance (5N)	ISO 4649	≤120	mm ²
	Compression set after 24h at 70 °C	ISO 815-1	≤30	%

TEMPERATURE

	Working temperature		-50/+80	°C
--	---------------------	--	---------	----

AGEING


	Δ Hardness after 168h at 70 °C	ASTM D573	≤7	Shore A
	Δ Tensile strength after 168h at 70 °C	ASTM D573	≤5	%
	Δ Elongation at break after 168h at 70 °C	ASTM D573	≤-20	%

CHEMICAL RESISTANCE

Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons
Good	Medium	Medium	Non suitable

IDENTIFICATION

Branding	Without.
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.
Wrapping	Black polyethylene film.
Labelling	Self-adhesive label indicating product name, dimensions, area in m ² , nominal weight, and product code to allow product traceability.

NR	NR SHEETING	RS12			
THICKNESS mm	WIDTH mm	LENGTH m	WEIGHT kg/m ²	SIDES FINISH	
1±0.3	1400±2%	20±2%	1.05	2 sides matt	
1.5±0.3	1400±2%	15±2%	1.58	2 sides matt	
2±0.3	1400±2%	15±2%	2.1	2 sides matt	
3±0.3	1400±2%	10±2%	3.15	2 sides matt	
4±0.4	1400±2%	10±2%	4.2	2 smooth sides	
5±0.4	1400±2%	10±2%	5.25	2 smooth sides	
6±0.5	1400±2%	10±2%	6.3	2 smooth sides	
8±0.7	1400±2%	5±2%	8.4	2 smooth sides	
10±1.0	1400±2%	5±2%	10.5	2 smooth sides	
12±1.0	1400±2%	5±2%	12.6	2 smooth sides	
15±1.0	1400±2%	5±2%	15.75	2 smooth sides	
20±1.4	1400±2%	5±2%	21	2 smooth sides	
25±1.75	1400±2%	5±2%	26.25	2 smooth sides	

